



TERRAZO TILES FOR INDOORS		UNE-EN 13748-1:05	
File number:	EH-100602	Sample Nr:	140150/1
Customer:	AZZO TILE AND ARCHITECTURAL PRODUCTS SOLUTIONS, LLC.		
Address:	PO BOX 1063 FORT LEE, NJ, 07024 (USA)		
Work:	Sef-Control Production-C.E Labelled		
Sample:	Monolayer Terrazo Tile of 16 x 16 x 0.8 in		
Origin:	Factory		
Reception Date:	01/16/2015	Test Date:	01/22/2015

DIMENSIONS

Tile Nr	Length (in)			Average(in)	Deviation from the average (%)	Deviation from the nominal (%)
	L1	L2	L3			
1	16.21	16.20	16.20	16.20	0.1	0.1
2	16.18	16.18	16.18	16.18	0.1	0.0
3	16.18	16.18	16.18	16.18	0.0	0.0
4	16.19	16.19	16.18	16.18	0.0	0.0
5	16.19	16.19	16.19	16.19	0.0	0.1
6	16.19	16.19	16.19	16.19	0.0	0.0
7	16.19	16.19	16.19	16.19	0.0	0.0
8	16.18	16.18	16.18	16.18	0.0	0.0

Average Length (in)	16.19	Max Length (in)	16.21
Nominal Length (in)	16.18	Min Length (in)	16.18

Tile Nr	Width (in)			Media (mm)	Deviation from the average (%)	Deviation from the nominal (%)
	G1	G2	G3			
1	16.22	16.21	16.21	16.21	0.2	0.2
2	16.18	16.18	16.18	16.18	0.0	0.0
3	16.19	16.19	16.19	16.19	0.0	0.0
4	16.18	16.18	16.18	16.18	0.0	0.0
5	16.18	16.18	16.18	16.18	0.0	0.0
6	16.18	16.18	16.18	16.18	0.0	0.0
7	16.18	16.18	16.18	16.18	0.0	0.0
8	16.19	16.19	16.19	16.19	0.0	0.0

Average Width (in)	16.19	Max Width (in)	16.22
Nominal Width (in)	16.18	Min Width (in)	16.18

Tile Nr	Thickness (in)			Average (in)	Deviation from the average (%)	Deviation from the nominal (%)
	E1	E2	E3			
1	0.75	0.76	0.71	0.74	3.6	4.4
2	0.72	0.69	0.67	0.70	2.7	1.9
3	0.73	0.74	0.73	0.74	2.8	3.7
4	0.71	0.75	0.72	0.73	1.7	2.6
5	0.69	0.71	0.72	0.70	1.4	0.6
6	0.67	0.71	0.72	0.70	2.3	1.5
7	0.68	0.69	0.71	0.69	3.1	2.2
8	0.71	0.71	0.73	0.72	1.4	2.2

Average Thickness (in)	0.72	Max Thickness (in)	0.76
Nominal Thickness (in)	0.71	Min Thickness (in)	0.67



AZZO TILE AND ARCHITECTURAL PRODUCTS SOLUTIONS, LLC.
PO BOX 1063 FORT LEE, NJ, 07024 (USA)
 Phone: (201)-731-4249
 e-mail: azzotile@gmail.com

File Nr:	EH-100602	Sample Nr:	140150/1
Customer:	AZZO TILE AND ARCHITECTURAL PRODUCTS SOLUTIONS, LLC.		
Address:	PO BOX 1063 FORT LEE, NJ, 07024 (USA)		
Work:	Sef-Control Production-C.E Labelled		
Sample:	Monolayer Terrazo Tile of 16 x 16 x 0.8 in		
Origin:	Factory		
Reception Date:	01/16/2015	Test Date:	01/22/2015

EDGES STRAIGHTNESS

Tile Nr	C1	C2	C3	L (in)	STRAIGHTNESS
1	0.0	0.0	0.0	16.20	0.0
2	0.0	0.0	0.0	16.18	0.0
3	0.0	0.0	0.0	16.18	0.0
4	0.0	0.0	0.0	16.19	0.0
5	0.0	0.2	0.0	16.19	0.0
6	0.0	0.0	0.0	16.19	0.0
7	0.0	0.0	0.0	16.19	0.0
8	0.0	0.0	0.0	16.18	0.0
Average Straightness (%)				0	
Maximum deviation				0	

FLATNESS OF THE EXPOSED FACE

Tile Nr	P1	P2		Average	(0.3%) Diagonal	Deviation (%)
1	0.0	0.0		0.00	1.75	0.00
2	0.0	0.0		0.00	1.74	0.00
3	0.0	0.0		0.00	1.74	0.00
4	0.2	0.0		0.10	1.74	0.10
5	0.1	0.1		0.10	1.74	0.00
6	0.1	0.1		0.10	1.74	0.00
7	0.1	0.0		0.05	1.74	0.05
8	0.3	0.2		0.25	1.74	0.05

CERTIFICATIONS:

QUALITY

ENVIRONMENT

